

WASHINGTON STATE BUILDING CODE

CHAPTER 51-50 WAC

INTERNATIONAL BUILDING CODE 2009 Edition

Includes adoption of and amendments to
the 2009 International Existing Building Code
and
ICC/ANSI A117.1-2003



Washington State Building Code Council

Effective July 1, 2010

2104.5 TMS 602/ACI 530.1/ASCE 6, Article 3.5 D, grout lift heights. Modify items 1.b, 1.c, and 2.b of Article 3.5 D as follows:

- 3.5 D.1.b When the conditions of Articles 3.5 D.1.a.i and 3.5 D.1.a.ii are met but there are intermediate bond beams within the grout pour, limit the grout lift height to the bottom of the lowest bond beam that is more than 5.33 ft. (1.63 m) above the bottom of the lift, but do not exceed a grout lift height of 12.67 ft. (3.86 m).
- 3.5 D.1.c When the conditions of Article 3.5 D.1.a.i or Article 3.5 D.1.a.ii are not met, place grout in lifts not exceeding 5.33 ft. (1.63 m).
- 3.5 D.2.b When placed in masonry that has not cured for at least 4 hours, place in lifts not exceeding 5.33 ft. (1.63 m).

2104.6 TMS 602/ACI 530.1/ASCE 6, Article 3.2F, cleanouts. Modify the first sentence of Article 3.2F as follows:

Provide cleanouts in the bottom course of masonry for each grout pour when the grout pour height exceeds 5.33 ft. (1.63 m).

(Insert Facing Page 434)